16 Date of					17
Receipt	Description of Sample	<u>From</u>	Result of Analysis	Reference	No
1923 April	Gold - various	Tomb of	Thickness varies from 0.01mm to 0.54mm	W. B. Arch 1/11	112
"	Faience Rings on Cloth Pad	Tut.ankh.amen	Cloth incrusted with crystals of common salt	W. B. Arch 1/14	113
"	Libation vessel No 69		SiO <sub>2</sub> or silicate, trace Na <sub>2</sub> CO <sub>3</sub> , little NaCl	WB Arch 1/16	114
"	Cover of libation vessel 54 (oo)		SiO <sub>2</sub> or insoluble silicate	WB Arch 1/16	115
"	-do- 54 x		SiO <sub>2</sub> or insoluble silicate	WB Arch 1/16	116
"	Faience vase No 25		See No 55		117
"	-do- No 31a		See No 63		118
"	-do- No 31b		See No 56		119
"	Faience ring		Cl present on incrustation	W. B. Arch 1/18	120
"	Necklace 21 u		Cl present on incrustation	W. B. Arch 1/19	121
"	Faience inlay on Box 44		Blue has darkened + become almost black	W. B. Arch 1/19	122
"	Cement from inlay		Resin	W. B. Arch 1/21	123
"	Colours from Glove No 92g		In holes where pattern has been coloured green	WB Arch 1/22	124
"	Bronze Arrow Heads		Slight corrosion only.	WB Arch 1/23	125
11	Stone Inlay		Is translucent fibrous calcite	W. B. Arch 1/24	126