

Date of Receipt	Description of Sample	From	Result of Analysis	Reference	No
1926					
Jan 2	Dust like material from face of coffin No 254 (2 nd)	Tut.ankh.Amen	Contains copper	WB Arch 5/11	6
" 2	Crystals from foot of coffin No 255 (3 rd)	"	Probably fatty acid	WB Arch 5/11	7
" 2	Cement from under glass in mask No 256A	"	Not in original condition. Not proceeded with	W.B. Arch 5/7	8
" 2	Cement from under stone in mask No 256A	"	Resin with red inorganic colouring matter not detd.	WB Arch 5/5	9
" 2	Filling from lapis lazuli scarab	"	Contains Pb and Cl.	W.B Arch 5/10	10
" 2	Cement from under inlay in mask No 256A	"	Not determined: sample too small	WB Arch 5/8	11
" 2	Black material from behind pupil of eye "	"	Possibly resin: sample too small	W.B. Arch 5/9	12
" 2	Gold nail from gold coffin	Tut.ankh.Amen	Weight 7.91 grams: fineness 18 carats (approx)	Cheml. Dept	15
" 2	Silver nail with gold head from 1 st . or 2 nd . coffin	"	Weight 10.09 grams: fineness gold 18 cts (approx): silver 600 (approx)	Cheml. Dept.	16
" 2	Gold 2 nd .Coffin	"	Thickness of Gold:(a) 0.04 to 0.07mm (b) 0.03 to 0.07mm (c) 0.05 to 0.07mm	Luxor Work Book	17
" 2	Glass (blue) 2 nd . coffin	"	In powder: this was alkaline + cont ^d a carbonate: no Cl or SO ₃	Luxor W.B.	18
" 2	Crystals from (a) skin of shoulders (b) loose in coffin No 255 of mummy	"	NaCl	Luxor W.B.	19